


Artículo/Article		SARGA CANIGO TECNOSANI		TEST ITEL CE-11340	
REUSABLE (>25 washes)		MADE IN SPAIN		TESTED (ACCORDING UNE-EN14683 and UNE-0065 CEE/93/42 ACABADO HIDROFUGADO Y ANTIBACTERIANO	
ANÁLISIS FÍSICO / PHYSICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Nº de Hilo/Thread Count	Urdimbre / Warp	20 1/C			
	Trama / Weft	20 1/C			
Densidad / Density	Urdimbre / Warp	96			
	Trama / Weft	57			
Ligamento / Weave	SARGA 2/1 S / TWILL 2/1 S				
Comp. Urd./ Comp. Warp	35% COTTON / 65% PES				ISO 1833:2006
Comp. Tr./ Comp. Weft	35% COTTON / 65% PES				
Total Comp.	35% COTTON / 65% PES			Simple: No tolerancia Compuesta: +/- 3%	
Ancho Final / Final Width	cm	150 / 160		+/-2%	ISO 3932:1976
Peso / Weight	gr/m ²	195 - 205		+/-5%	ISO 3801:1977
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre	pass	kgf	EN-13795
		Trama	pass	kgf	
Resistencia Abrasion	pass				EN-13795
Resistencia Desgarro / Tear	Urdimbre/Warp (G)	N/A	Trama / Weft	N/A	EN-13795
Encogimiento / Shrinkage	°C	60	% Urdimbre	+/- 2	0 - 3 %
			% Trama	+/- 2	
SPECIAL MEDICAL TESTS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Washing solidity 60°C	5			0-5	UNE EN ISO-05
Pilling	5			0-5	UNE EN ISO 12945-2
Traspirability	< 60 Pa/cm ²				AST1
Aerosol Filtration Efficiency	>94%				UNE EN14683
Particle Filtration Efficiency	>94%				UNE EN14683
Particle Filtration	0,4 micras and >96% efficiency				UNE EN149
Bacterial presence	DRY: PASS	WET: PASS			EN-13795
ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
pH	Conforme/According Oeko-Tex II			4,0 - 7,5	UNI EN ISO 3071/06
Formaldehído	Conforme/According Oeko-Tex II		<16ppm	<75ppm	UNE EN ISO 14184-1:1999
Arlaminas	Conforme/According Oeko-Tex II			20 ppm	UNE 2002/61/CE
PROHIBIDOS / FORBIDDEN					
Metales Pesados	Conforme/According Oeko-Tex II		Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm		
AZO Colorants	Conforme/According Oeko-Tex II		No detectable		
Colorantes Alérgicos	Conforme/According Oeko-Tex II		No detectable (LMBG) (1/4/96)		
SÍMBOLOS DE LAVADO / WASH CARE SYMBOLS					
Observaciones:					
TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO					
AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT					
NO USAR LEJIA / DO NOT USE BLEACHING					
PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS					
GRS POST CONSUME bajo pedido / on request					